

GREASES

Technical Data Sheet



ELPRIMO LX 150-EP

PRODUCT DESCRIPTION:

ELPRIMO LX 150-EP is a lithium complex-based grease designed for both industrial and automotive applications. It is specifically formulated to withstand high temperatures and provide long-lasting performance. This versatile grease offers excellent protection against fretting corrosion and water washout, along with reliable corrosion protection and mechanical stability. With EP, rust, and anti-oxidant additives, ELPRIMO LX 150-EP provides superior load-carrying capabilities for various lubrication needs.

APPLICATIONS

This product is suitable for grease-lubricated bearings at low and high speeds including electric motors, automotive bearings, and various anti-friction bearings in the mining, petrochemical, construction, and steel industries. It has good pumpability properties and can be used in centralized lubrication systems.

PRODUCT ADVANTAGES

- · Good high-temperature stability
- Extreme pressure capability
- · Resistance to water washout

- · Excellent rust and corrosion protection
- · Long service life

TYPICAL PROPERTIES:

| PARAMETERS | TEST METHODS | TYPICAL VALUE | | |
|---|--------------|------------------------|------------------------|------------------------|
| NLGI Grade | - | | 2 | |
| Thickener Type | - | Lithium complex | Lithium complex | Lithium complex |
| Apprearance | Visual | Smooth & Homogenous | Smooth & Homogenous | Smooth & Homogenous |
| Work penetration @25°C, | ASTM D217 | 310 - 340 | 265 - 295 | 220 - 250 |
| Copper Strip Corrosion for 24hrs @100°C, | ASTM D4048 | 1b max. | 1b max. | 1b max. |
| Dropping Point °C, | ASTM D566 | >250 | >250 | >250 |
| Wheel Bearing leakage after 6hrs @ 105°C g, | ASTM D1263 | max 5 | max 5 | max 5 |
| Base Oil Viscosity @ 40 °C (cSt) | ASTM 445 | 150 | 150 | 150 |
| Four Ball EP, Load Wear Scar, mm | ASTM D2266 | 0.6 | 0.6 | 0.6 |
| Four Ball Weld Lead Kgf, Min | ASTM D2596 | 250 | 250 | 250 |
| Water Washout resistance %WT @79°C, | ASTM D1264 | max 5 | max 5 | max 5 |
| Oil separation %, 30hrs @100°C, | ASTM D6184 | max 5 | max 5 | max 5 |

HEALTH & SAFETY, ENVIRONMENT:

Prolonged and repeated contact with grease may cause skin disorders. Avoid contact. Wash immediately with soap and water. Do not discharge used grease in to drains or the environment. For further Information on Safety Guidelines please refer to MSDS available on our website www.bravoil.ae

HEALTH & SAFETY:

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office or via the internet www.bravoil.ae

PROTECT THE ENVIRONMENT:

Comply with local regulation. Do not discharge into drains, soil or water.

STORAGE

We recommend to store all packages under cover. In case outside storage is unavoidable, drums should be laid horizontally to avoid the possible ingress of water and damage to drum markings. Products should never be stored above 60°C, exposed to hot sun or freezing conditions.

226 Version: 01-2023 _______ inquiry@bravoil.ae bravoil.ae