

Technical Data Sheet

GREASES



# ELPRIMO LX 220-EP

## PRODUCT DESCRIPTION:

ELPRIMO LX 220-EP grease is made from high viscosity index mineral oils and performance additives to enhance extreme pressure, anti-wear, anti-corrosion, and anti-oxidation properties. This grease is recommended for bearings operating under the load at high temperatures. This product is also suitable for use in applications such as continuous casting, quarries, breakers, roller conveyors, and automotive wheel bearings.

#### **APPLICATIONS:**

ELPRIMO LX 220-EP is recommended for bearings operating under the load at high temperatures. It is also suitable for use in applications such as continuous casting, quarries, breakers, roller conveyors, and automotive wheel bearings.

## PRODUCT ADVANTAGES

- The operating temperature range is from -25°C to 140°C
- · Excellent mechanical stability under vibrating conditions
- · Excellent extreme pressure properties
- Excellent wear resistance
- High dropping point
- Good corrosion protection

## TYPICAL PROPERTIES:

| PARAMETERS                                      | TEST METHODS | TYPICAL VALUE          |                        |                        |
|---|--------------|------------------------|------------------------|------------------------|
| NLGI Grade                                      | -            | 1                      | 2                      | 3                      |
| Thickener Type                                  | -            | Lithium complex        | Lithium complex        | Lithium complex        |
| Apprearance                                     | Visual       | Smooth &<br>Homogenous | Smooth &<br>Homogenous | Smooth &<br>Homogenous |
| Color   | Visual       | Blue / Red / Natural   |                        |                        |
| Work Penetration @25°C                          | ASTM D217    | 310-340                | 265 - 295              | 220 - 250              |
| Copper Strip Corrosion 24hrs @100°C             | ASTM D4048   | 1b max.                | 1b max.                | 1b max.                |
| Dropping Point °C, Min                          | ASTM D2265   | 240                    | 240                    | 240                    |
| Water Washout Resistance %Wt @79°C              | ASTM D1264   | max 5                  | max 5                  | max 5                  |
| Four Ball, Load Wear Scar, Mm                   | ASTM D2266   | 0.6                    | 0.6                    | 0.6                    |
| Four Ball Weld Load, Kgf, Min                   | ASTM D2596   | 250                    | 250                    | 250                    |
| Wheel Bearing Leakage After 6hrs @ 105°C,<br>gm | ASTM D1263   | max 8                  | max 8                  | max 8                  |
| Oil Separation, % 30hrs @100°C                  | ASTM D6184   | max 5                  | max 5                  | max 5                  |
| Operating Temperature Range, °C                 | INTERNAL     | -25 to 140             |                        |                        |
| Base Oil Viscosity @40°C (Cst)                  | ASTM 445     | 220                    | 220                    | 220                    |

#### HEALTH & SAFETY, ENVIRONMENT:

Prolonged and repeated contact with grease may cause skin disorders. Avoid contact. Wash immediately with soap and water. Do not discharge used grease in to drains or the environment. For further Information on Safety Guidelines please refer to MSDS available on our website www.bravoil.ae

#### HEALTH & SAFETY:

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office or via the internet www.bravoil.ae

#### PROTECT THE ENVIRONMENT:

Comply with local regulation. Do not discharge into drains, soil or water.

## STORAGE:

We recommend to store all packages under cover. In case outside storage is unavoidable, drums should be laid horizontally to avoid the possible ingress of water and damage to drum markings. Products should never be stored above 60°C, exposed to hot sun or freezing conditions.